



Formolene® HF4202

High Density Polyethylene (HDPE) Resin for Film Extrusion Applications

Formolene® HF4202 is a hexene based linear low density film grade designed for blown film extrusion applications requiring good strength and stiffness. Films exhibit good tensile and puncture resistance properties.

Suggested Applications:

Agricultural film Diaper Backsheet Overwrap films

Additives:

Antiblock - No Slip – No Processing Aid - No

Nominal Values

PROPERTY*	ASTM TEST METHOD	ENGLISH		SI	
		Unit	Value	Unit	Value
Density	D1505	g/cc	0.942	g/cc	0.942
Base Resin Density (without additives)	D1505	g/cc	0.942	g/cc	0.942
Melt Index, (190°C/2.16)	D1238	g/10 min.	2.0	g/10 min.	2.0
Film Properties					
Tested Film Thickness		mil	1.0	µm	25
Tensile Strength					
Yield, MD	D882	psi.	2500	MPa	17
Yield, TD		psi.	3300	MPa	23
Break, MD		psi.	7100	MPa	49
Break, TD		psi.	6000	MPa	41
Tensile Elongation					
Break, MD	D638	%	770	%	770
Break, TD		%	930	%	930
Dart Drop Impact	D1709A	g	< 50	g	< 50
Elmendorf Tear Strength					
MD	D1922	g	20	g	20
TD		g	110	g	110
Optical Properties					
Gloss (45°)	D2457		40		40
Haze	D1003	%	18	%	18

Note: Film Properties based on screw size of 2.5 in.; 30:1 ratio L/D and with a 2.5:1Blow Up Ratio. Actual film properties may vary depending on operating conditions and additive packages. Film properties are not intended to be used as specifications.

Published 01/10/2023

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (800) 363-1823 • Fax: (973) 716-7483

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA INDUSTRIES CORPORATION and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA INDUSTRIES CORPORATION MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statement herein, therefore, should not be construed as representations or warranties. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.

Formolene® is a registered trademark of Formosa Plastics Corporation, U.S.A. Formosa Industries Corporation is an authorized user of this trademark.