



Formosa Industries

Formolene® HDPE

Formolene® HJ5207

High Density Polyethylene (HDPE) Resin for Injection Molding

Formolene® HJ5207 is a hexene based injection molding resin designed for toughness and stiffness.

Formolene® HJ5207 meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact.

Suggested Applications:

Industrial Pails Industrial Caps & Closures

Additives:

Antioxidant – Yes

Nominal Values

PROPERTY*	ASTM TEST METHOD	ENGLISH		SI	
		Unit	Value	Unit	Value
Density	D1505	g/cc	0.952	g/cc	0.952
Melt Index, (190°C/2.16)	D1238	g/10 min.	6.5	g/10 min.	6.5
Molded Properties					
Tensile Strength					
Yield	D638	psi.	3800	MPa	26
Tensile Elongation					
Break	D638	%	1300	%	1300
Flexural Modulus	D790B				
1% Secant		psi.	190000	MPa	1300
2% Secant		psi.	160000	MPa	1080
Environmental Stress Crack Resistance	D1693B				
10% Igepal, F50		hr	4	hr	4
Notched Izod Impact (-40°F)	D256A	Ft-lb/in.	0.92	J/m	49

Note: All properties were derived from compression molded specimens. Actual properties may vary depending on operating conditions and additive packages. Properties are not intended to be used as specifications.

Published 11/1/2019

Any inquiries regarding this data sheet should be addressed to: 9 Peach Tree Hill Road • Livingston, NJ 07039 • Phone: (800) 363-1823 • Fax: (973) 716-7483

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of FORMOSA INDUSTRIES CORPORATION and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting the results, FORMOSA INDUSTRIES CORPORATION MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statement herein, therefore, should not be construed as representations or warranties. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.

Formolene® is a registered trademark of Formosa Plastics Corporation, U.S.A. Formosa Industries Corporation is an authorized user of this trademark.